

Peran STB



A durable, industrial flooring system consisting of coloured quartz granules encapsulated in a clear resin binder.



The applied colours may differ from the examples shown.
For a full colour chart and samples, contact your local CPG Europe office.

Peran STB Color marking method:

The first digit in the color number is the size of the sand.
Each color is available in 3 sizes of sand. Sand no. 5 - size about 1.8 mm, sand No. 7 - size about 1.2 mm, sand No. 8 - size about 0.8 mm.
For example, the Peran STB in Grey 5100 contains Sand no. 5 and the Peran STB in Grey 7100 - sand no. 7.

Technical Information¹

REACTION TO FIRE	
B _n -s1	EN 13501-1
SLIP RESISTANCE ²	
Dry > 40 wet > 40 (anti-slip ver.)	EN 13036-4
TEMPERATURE RESISTANCE	
Sustained heat: +60°C, intermittent spillages: +70°C	
WATER PERMEABILITY	
Karsten test - Nil (Impermeable)	
SURFACE HARDNESS	
SH 100	EN 13892-6
WEAR RESISTANCE	
Class AR0,5	PEN 13892-4
COMPRESSIVE STRENGTH	
> 75 N/mm ²	EN 13892-2
FLEXURAL STRENGTH	
> 30 N/mm ²	EN 13892-2
TENSILE STRENGTH	
> 15 N/mm ²	BS 6319
IMPACT RESISTANCE	
IR20	EN ISO 6272-1
BOND STRENGTH	
3,0 MPa	EN 13892-8
VAPOUR PERMEABILITY	
1,36 g/m ² /mm/24h	ASTM E96:60



High mechanical resistance:

High scratch and abrasion resistance, excellent wear and impact resistance



High chemical resistance:

Protects against the majority of chemicals



Anti-slip finish:

Slip resistant finish can be tailored to specific client requirements



Hygiene:

Seamless – easy to clean

¹The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site. ²The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from CPG Eastern Europe), the degree of abrasion, maintenance and the nature of the dirt.

Model Specification

System:	Peran STB
Finish:	Gloss or Matt
Thickness:	approx. 2–6 mm
Colour:	According to the catalog
Producer:	CPG Europe
Supplier:	Tremco CPG Poland Sp. z o.o.
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting CPG Eastern Europe or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System³

Primer:	Peran STC or Protop 1000; Colour quartz sand
Topping:	Peran STC or Protop 1000; Peran SL C; Colour quartz sand
Topcoat:	Peran STC
Matt finish (optionally):	matt sealer

³ If other resins are used contact CPG Eastern Europe for further details.

Detailed application instructions are available upon request.


Speed of cure

	10 °C	20 °C	30 °C
Light Traffic	36 hrs	24 hrs	12 hrs
Full traffic	72 hrs	48 hrs	24 hrs
Full chemical cure	12 days	7 days	5 days

Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% humidity measured by the Tramex method) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

System Design



Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Tremco CPG Poland Sp. z o.o. (further related as „CPG Polska”) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer’s control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, CPG Polska cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized CPG Polska representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact CPG Polska.

25/05/21

CPG Eastern Europe
ul. Marywilska 34, 03-228 Warsaw, Poland
tel.: +48 22 879 8907
email: poland@cpg-europe.com

 **Construction
Products Group**
Europe

www.flowcrete.com.pl